

Novinox® PAZ

in long oil alkyd DIY system

Guiding formulation/REF 012118ML2 Dry film thickness: **80µm**
SETAL 270 Application over **CRS** using a spray gun
 Salt spray resistance **900hrs** on CRS according to the ASTM B-117

RAW-MATERIALS	% WEIGHT	DESCRIPTION	SUPPLIERS
<i>Mix in the following order</i>			
SETAL 270	40.0	Long oil alkyd (length : 65%)	NUPLEX
VAR SOL 40	7.9	Aliphatic solvent blend	EXXON CHEMICALS
SOJA LECITHIN	0.2		
BENTONE SD2	0.2	Rheological additive	ELEMENTIS SPECIALITIES
<i>mix until homogeneous preparation</i>			
TiO ₂ RTC90	19.5	Rutile	HUNSTMANN
Novinox® PAZ	5.0	Anticorrosive pigment	SNCZ
DURCAL 2	5.0	Calcium carbonate	OMYA
THIXATROL ST	0.2	Thixotropic additive	ELEMENTIS SPECIALITIES
<i>mill grind 40 minute through 6 on a Hegman gauge</i>			
SETAL 270	12.9	Long oil alkyd	NUPLEX
VAR SOL 40	6.2	aliphatic solvent blend	EXXON CHEMICALS
NUODEX 8% Co	0.6	Drier	ELEMENTIS SPECIALITIES
NUODEX 10% Zr	2.1	Drier	ELEMENTIS SPECIALITIES
MEKO	0.2	Antiskinning agent	
TOTAL WEIGHT	100		



45/49, Chaussée Jules César – F-95250 Beauchamp

Technical support : tech.support@sncz.net

Tél : +33 1 30 40 57 57

www.sncz.com

Properties

PVC % :	21.24
Solids % :	67.94
Volumic solids % :	49.25
Pigment/Binder ratio (vol) :	0.36

The information herein is general information designed to assist customers in determining whether our products are suitable for their applications. We require customers to check the suitability of our products for their specific application. We cannot accept liability for the application and processing of our products where it lies out of our control.