

Novinox PPS10

In SB acrylic primer 2K

Guiding formulation/REF 100304ML5
MACRYNAL SM548/50x DESMODUR N75

Dry film thickness: **80 µm + 120µm**
Application over **CRS** using a spray gun
Salt spray resistance **650hrs** according to the ASTM B-117

RAW-MATERIALS	% WEIGHT	DESCRIPTION	SUPPLIERS
<u>PART A</u>			
<i>Mix in the following order</i>			
MACRYNAL SM548/50x	31.20	Acrylic resin	ALLNEX (CYTEC)
DOWANOL PMA	13.00	Glycol ester, solvent	DOW CHEMICALS
<i>Mix until homogeneous preparation</i>			
TiO ₂ TR92	9.40	Rutile	HUNSTMANN
Novinox® PPS10	4.20	Anticorrosive pigment	SNCZ
BaSO ₄	23.81	Filler	OMYA
TALC 10M2	5.20	Filler	IMERYS
<i>Grind for 40 minutes till 5 on a Hegman gauge</i>			
NUODEX Zn 8%	0.13	Catalyst agent	ELEMENTIES SPECIALTIES
DBTL	0.06	Catalyst agent	ALLNEX (CYTEC)
<u>PART B</u>			
DESMODUR N75	7.80	Polyisocyanate hardener	BAYER
DOWANOL PMA	5.20	Glycol ester, solvent	DOW CHEMICALS
TOTAL WEIGHT	100		



45/49, Chaussée Jules César – F-95250 Beauchamp
Technical support : tech.support@sncz.net
Tél : +33 1 30 40 57 57
www.sncz.com

Properties

PVC % :	36.19
Solids % :	64.19
Volumic solids % :	42.97
Pigment/Binder ratio (vol) :	0.57

The information herein is general information designed to assist customers in determining whether our products are suitable for their applications. We require customers to check the suitability of our products for their specific application. We cannot accept liability for the application and processing of our products where it lies out of our control.