

# Novinox PAZ

## in wash primer 2K

Guiding formulation/REF 201004ML2 BI  
MOWITAL B30H

RAW-MATERIALS	% WEIGHT	DESCRIPTION	SUPPLIERS
<b>PACK ONE</b>			
<i>Mix in the following order</i>			
<b>SOLUTION A</b>			
PHENODUR 263/70B	7.90	Phenolic binder	ALLNEX
N BUTANOL	3.00	Solvent	SHELL
ISOPROPYL ALCOHOL	14.00	Solvent	SHELL
Dispersing agent	0.15		
<b>Novinox® PAZ</b>	<b>9.50</b>	<b>anticorrosive pigment</b>	<b>SNCZ</b>
TALC 10M2	3.01	Filler	IMERYS
AEROSIL R972	0.36	Filler	EVONIK
LANCO PE1500F	0.08	Polyethylene wax	LUBRIZOL
BENTONE 10% IN XYLENE	1.52	Rheological additive	ELEMENTIS SPECIATIES
<i>mill grind for 1h through 7 on a Hegman gauge</i>			
<b>SOLUTION B</b>			
MOWITAL B30H	9.49	Polyvinylbutyral binder	KURARAY
ISOPROPYL ALCOHOL	20.92	Solvent	SHELL
N BUTANOL	3.23	Solvent	SHELL
TOLUENE	3.19	Solvent	SHELL
<i>Mix Until homogeneous solution</i>			
<b>PACK TWO</b>			
<b>SOLUTION D</b>			
WATER	1.31		
80% PHOSPHORIC ACID	2.29		
ISOPROPYL ALCOHOL	18.10	Solvent	SHELL
N BUTANOL	1.95	Solvent	SHELL
<b>TOTAL WEIGHT</b>	<b>100</b>		
<b>Preparation</b> Slowly mix pack two with pack one, pot life: 6h.			



45/49, Chaussée Jules César – F-95250 Beauchamp

Technical support : [tech.support@sncz.net](mailto:tech.support@sncz.net)

Tél : +33 1 30 40 57 57

[www.sncz.com](http://www.sncz.com)

### Properties

PVC % :	24.42
Solids % :	29.13
Volumic solids % :	17.26
Pigment/Binder ratio (vol) :	0.32

The information herein is general information designed to assist customers in determining whether our products are suitable for their applications. We require customers to check the suitability of our products for their specific application. We cannot accept liability for the application and processing of our products where it lies out of our control.

20/08/2013  
Gf\_113\_v0.01